




Superior
Manufacturing
Group, Inc.

656 Niru® Cushion-Ease® Solid

Anti-Fatigue/Anti-Slip Matting



Available Colors: Black
(Shown with Yellow M.D. Ramps)



Niru® Cushion-Ease® Solid is made with a 100% Nitrile rubber compound providing unmatched durability and performance in harsh wet environments where caustic chemicals, cutting fluids, animal fats, oils, and greases are often found. A solid top construction offers additional anti-fatigue relief, and is easy to clean. Easy to snap together mats are compatible with NoTrax M.D. Ramp System for on-site custom configurations.

Test	Test Description	*Results
Compression Deflection	Test specimen is subjected to varying compression load levels and the resulting deflection was measured. The greater the deflection, the better the anti-fatigue properties. (Inches)	.063" (20 lbs/sq. inch) .112" (40 lbs/sq. inch)
Coefficient of Friction ASTM C1028-96	A neolite heel assembly with a predetermined load is pulled horizontally with a dynamometer to measure the force required to cause the assembly to slip.	.85
Abrasion Resistance ASTM D3884-01	Test specimen is subjected to the rubbing action of two abrading wheels under controlled conditions. Results measured in Weight loss (Grams)	1.0 Grams (1.2%)
Elongation ASTM D412	Test specimen is stretched at a specified rate until breaking point. The results are measured in weight needed to break, and % of size increase at breaking point.	60.1 lbs 451.8% (average of 5 specimens)
Hardness ASTM D2240-02	The hardness of a test sample is measured by means of a type A Shore Durometer. It measures the penetration of its specified indenter forced into the material under specified conditions	50

*All testing of NoTrax® floor matting has been performed by an independent testing laboratory.



Anti-Fatigue



Anti-Slip




Food Processing



Welding

- 100% Nitrile rubber compound: provides the highest degree of resistance to chemicals, oils, and greases
- Thickness: 3/4"
- Stock Sizes: 3' x 3'
- Compatible with patented M.D. Ramp System



RESULTS from INDEPENDENT TEST LABS & PRESENTED as COMPARISONS to OTHER NoTRAX® INDUSTRIAL MATS